



## HERITAGE

SPC FLOORING: UNICLIC / UNIPUSH™ CLICK SYSTEM

### UV SURFACE TREATMENT: Thickness In Microns

- Super Stain And Scratch Resistant
- Completely Waterproof
- No Bugs No Termites

### TRANSPARENT WEAR LAYER: 0.55 mm

- Enhances the Color And Embossing
- Protects From Abrasion

OVER ALL THICKNESS: 5.50 mm



### FILM LAYER: 0.10 mm

- Elegant Wood Designs
- Natural Looking, Natural Feeling

### RIGID CORE: 3.35 mm

- Sturdy Construction
- Dimensional Stability
- Uniclic™ / Unipush™ Click System
- Quick And Easy Installation

### IXPE Backing: 1.50 mm

- 1.50 mm IXPE Backing With Good Grip
- Insulates Sound
- Provides Underfoot Comfort

## FEATURES & BENEFITS

## APPLICATIONS



Superior Scratch & Stain Resistant



No Bugs & Termites



Click Installation  
No Adhesive



100%  
Waterproof



Easy  
Clean



Multiple Color  
Combinations



Corporate Offices



Residential



Natural Looking  
Design



Zero  
Maintenance



Superb  
Dimensional  
Stability



Endures  
Medium  
Foot Traffic



Excellent  
Sound  
Insulation



No Sub-Floor  
Required



Retail



Hospitality



## SPC FLOORING: UNICLIC / UNIPUSH™ CLICK SYSTEM

SPC FLOORING FOR HEAVY COMMERCIAL USE | PUR Polyurethane Reinforcement | Product Standard **HERITAGE** ASTM F3261-17

CERTIFICATION & CLASSIFICATION	STANDARD	HERITAGE
TYPE OF FLOOR COVERING	ASTM F3261   EN 16511	RESILIENT FLOORING IN MODULAR FORMAT WITH RIGID CORE (SPC)
CE CERTIFICATION	EN 14041	YES
CLASSIFICATION	EN ISO 10874	HEAVY TRAFFIC : CLASS 34

TECHNICAL CHARACTERISTICS	STANDARDS	HERITAGE
TOTAL THICKNESS	EN ISO 24336 (EN 428)	5.50 MM
WEAR LAYER THICKNESS	EN ISO 24340 (EN 429)	22 MIL WL   0.55 MM
SURFACE TREATMENT	UV TREATED	PUR
TOTAL WEIGHT	EN ISO 23997 (EN 430)	1.72 LBS / SQ FT = 8.40 KG / m <sup>2</sup>
WEAR LAYER BINDER CONTENT	ISO 10582	TYPE I
FORM OF DELIVERY	EN ISO 24342 ( EN 427 ) PLANKS IN CARTON	7" X 48" = 21.02 SF / CARTON
		178 mm X 1219 mm = 1.95 m <sup>2</sup> / CARTON
	PIECES	9 PIECES PER CARTON
	EDGE FINISH	PAINTED BEVEL

TECHNICAL PERFORMANCES	STANDARDS	HERITAGE
DIMENSIONAL STABILITY	EN ISO 23999 ( EN 434)	< 0.10%
REACTION TO FIRE	EN 13501 – 1	BFL- S1   PASS
RESIDUAL INDENTATION	EN ISO 24343-1 (EN 433)	REQUIRED VALUE : < 0.10 MM AVERAGE MEASURED VALUE : 0.03 MM
FURNITURE LEG	EN 424	NO DAMAGE
CASTOR CHAIR	EN ISO 4918 (EN 425)	NO DAMAGE
CURL RESULTANT TO HEAT	EN ISO 23999 (434)	< 2MM   PASS
IMPACT SOUND REDUCTION	EN ISO 140-8 EN ISO 717/2	Δ LNW = 21 DB
LIGHT FASTNESS	EN ISO 105 – B02	PASS
RESISTANCE TO CHEMICALS	EN ISO 26987 (EN423)	GOOD RESISTANCE   PASS
SLIP RESISTANCE	DIN51130   EN 13893	R9   PASS
STATIC LOAD	ASTM F970 / F387	PASS



**ISO 9001**  
**ISO 14001**  
**ISO 18001**



EN 14041

